



# Peeling layers: set slower initial layer

Some filament seems to be more sensitive for this issue. Trying to adjust the temperature compounded problems.



The solution seems to be to slow down the initial layer. From 50mm/s to 30mm/s



Revision #1

Created 17 November 2024 12:49:56 by Tim

Updated 17 November 2024 12:56:28 by Tim